

## ＜ 大同化成工業（株）の取扱い顔料一覧 ＞



An idiomatic Name	Color Index No. ( C. I. Pigment )	Products ( Name )	Fastness Properties *2							Recommended Applications *3					Characteristic
			Light Fastness	Heat Resistance °C	Water Resistance	Solvent Resistance	Acid Resistance	Alkali Resistance	Inks		Paints		Plastics and rubbers		
									Offset inks	Solvent-base inks	Water-base inks	Air Drying Paints		Metal Plate	
Tartrazine Lake - Al	Yellow 100	NO.3800 YELLOW LAKE	1	-	3	3	2	2	○				○		For Inner metal plate
Sunset Yellow Lake - Al	Yellow 104	NO.3850 YELLOW LAKE	1	-	4	5	3	2	○				○		For Inner metal plate
Lake Red C - Ba	Red 53:1	NO.4010 LAKE RED C	4	140	4	4	3	2	◎	◎				○	General grade
Lake Red C - Ba	Red 53:1	NO.4040 LAKE RED C	4	140	4	4	3	2	◎	◎				○	Good transparency
Permanent Red 2B - Ba	Red 48:1	NO.621 HELIO FAST RED LT	4	170	4	4	3	2	◎	◎		○		○	Yellowish red
Permanent Red 2B - Ca	Red 48:2	NO.630 WATCHUNG RED	5	170	4	4	3	2	◎	◎		○		○	Bluish red
Permanent Red 2B - Sr	Red 48:3	NO.5500 ST-RED	4	170	4	4	3	3	◎	○					Good dispersibility for offsetinks
Brilliant Carmine 6B - Ca	Red 57:1	---	5	160	4	4	3	2	◎	○	○			○	We have various grades. Please, contact us.
Bordeaux 10B - Ca	Red 63:1	NO.86 BORDEAUX 10B	5	150	4	5	3	2	○	○					Bluish red
Rhodamine 6G Lake - PMT *1	Red 81:4	NO.9310 PINK	5	150	5	5	3	3	○		○				Vivid color
Rhodamine B Lake - PMT	Violet 1	NO.409 NEO FANAL BOTAN	5	150	4	4	3	3	○		○				Characteristic color
Methyl Violet Lake - PMT	Violet 3	NO.101 NEO VIOLET LAKE	4	150	4	5	3	3	○		○				Vivid color
Methyl Violet Lake - Tannin	Violet 3:3	NO.4 VIOLET LAKE	1	-	3	3	2	2	○		○				Economical Grade
Victoria Blue Lake - PMT	Blue 1	NO.20 FANAL BLUE	4	150	4	5	3	3	◎		○				Vivid color
Treated Carbon Black	Black 7	NO.9945 BLACK	5	200	5	4	5	4	○	◎					Special carbon glade

\*1) PMT = Phosphorus, Molybdenum, Tungsten

\*2) Poor 1 ← → 5 Excellent

\*3) ◎:Excellent ○:Good

Ver.w1.3 2020/07/20

※ 上記顔料は当社取り扱い製品、代表グレードの一部です。ご要望につきましては、別途、お伺いいたしますので、お気軽にお問い合わせ下さい。

ここに記載されている内容は、細心の注意を払って確認されたものですが、保証値ではありません。